

A high performance two part epoxy grout for dynamic/repetitive load applications suitable for large volume pours

Uses

Conbextra EP120 is for use in situations where heavy dynamic or mobile loads are encountered. The gap between a base plate and substrate needs to be filled and the structural load be uniformly distributed.

Applications

- Reciprocating machinery
- Testing equipment
- Heavy crane and transporter rails
- High speed turbines
- Centrifuges and drop forges.

Also for use in conditions where chemical spillage may be encountered. Typical situations could be met in steelworks, refineries, electroplating works and chemical plants.

Conbextra EP120 is especially suitable where long working time and/or low exotherm properties are required e.g. for large pours or high ambient temperatures. It can also be used for grouting wide gap ranges making it a versatile product for a number of applications.

Advantages

- High compressive, tensile and flexural strengths
- Resistant to repetitive dynamic loads
- Fast, convenient installation
- Withstands a wide range of chemicals
- Virtually no shrinkage and hence ensures complete surface contact and bond
- Low creep characteristics under sustained loading
- Excellent flow properties
- Two part material giving a better quality control during mixing
- Can be used installed at high temperatures
- Wide range of gap thicknesses are possible

Description

Conbextra EP120 is unique two part epoxy grout formulation which does not require any additional aggregate to be added. This saves time and labour in the mixing process and provides a higher quality control in the mixing and placing of the grout.

Design Criteria

Conbextra EP120 is designed to be grouted into gaps from 10mm up to 120mm. Grouting of gap widths below 50mm will take longer to cure due to the low exotherm nature of the grout. If a fast cure of the grout is critical at smaller gap widths please refer to the Conbextra EP65 Plus technical data sheet.

Grout pours greater than 120mm thick are also possible but care should be taken that the total volume of the single pour should be no greater than 1m³. Consult Fosroc for further advice.

Chemical Resistance

Conbextra EP120 is resistant to oil, grease, fats, most chemicals, mild acids and alkalis, fresh and sea water. Consult Fosroc Technical Services when exposure to solvents or concentrated chemicals is anticipated.

Fosroc® Conbextra EP120

Properties

The following results were obtained at a temperature of 23°C unless otherwise stated.

Test Method	Standard	Test Result				
Density		1700 kg/m ³				
		Cure Time	10°C	23°C	30°C	40°C
Compressive Strength (MPa)	AS1478.2 2005	1 day	0	6	19	38
		3 days	5	45	55	68
		7 days	45	75	80	85
		28 days	70	80	85	85
		56 days	80	85	85	85
Indirect Tensile Strength	AS1012.2 10-2000	28 days - 10MPa				
Flexural Strength (Modulus of Rupture)	AS1012.2.11-2000	28 days - 25MPa				
Modulus of Elasticity	AS 1012.17-1997	8.4 GPa				
Thermal Coefficient of Expansion	ASTM C531:2000	1.06 x 10 ⁻⁴ mm/mm °C				
Slant Shear Bond Strength	ASTM C882/ C882M:2012	22.3 MPa (bond failure)				
Creep 28 days @ 2.8MPa	ASTM C1181-00	@ 23°C 1.7 x 10 ⁻³ cm/cm @ 60°C 2.1 x 10 ⁻² cm/cm				
Chloride Content	EN 1015-17:2000	0.0%				
Pot Life		10°C	6 hours			
		20°C	3 hours			
		30°C	1.5 hours			
Colour		Charcoal grey (mixed)				
Minimum Thickness		10mm				
Maximum Thickness		120mm				

Note: Compressive strengths stated above were measured using cube samples. Test results obtained will vary if testing is carried out to an alternative standard or sample dimensions are used. Refer to the compressive strength testing guide for epoxy grouts document for further information.

Flow characteristics

The maximum distance of flow is governed by the gap thickness, the head of grout applied and the ambient temperature. The following table gives typical data for flow design.

	Temperature (°C)	Gap Thickness (mm)	Hydrostatic head (mm)	Maximum Flow
Conbextra EP120	5	10	100	600
	5	35	100	700
	20	10	100	750
	20	35	100	2000
	30	10	100	950
	30	35	100	2500

Fosroc®

Conbextra EP120

Application Instructions

The following instructions for use should be used in conjunction with the Conbextra Epoxy Grouting Applications Guide.

Foundation surface

All contact surfaces must be free from oil, grease, free standing water or any loosely adherent material. Concrete surfaces should be cut back to a sound base. All dust must be removed and bolt holes or fixing pockets blown clean of any dirt or debris.

Steel surfaces

All steel surfaces should be shot blasted free of rust, paint and flaky mill scale.

Formwork

The formwork should be constructed to be leakproof as Conbextra EP120 is a free flowing grout. Loss of grout once the material is placed, but not hardened, will result in incomplete filling of the gap.

For free flow grout conditions it is essential to provide a hydrostatic head of grout. To achieve this a feeding hopper system should be used.

Forming materials should be coated with a release agent such as grease or wax material or a plastic coating. These coatings act as a bond breaker so that a smooth grout surface is achieved after form removal and the forms are protected for reuse.

Mixing

Pour all the contents of the hardener pack into the base container. A forced-action mixer is essential. Mixing at a slow speed (400/500 rpm) for 3 to 5 minutes using appropriate equipment such the Ransom 140 x 600 M14 Helical mixing paddle (product code: N4020892-UNIT) fitted to a heavy-duty 1600W mixer, such as Ransom 1602 E (product code: NP7EV160-UNIT) or equivalent is acceptable for small volume mixes. For large pours a purpose made grout mixer / pump may be used.

Ensure the paddle is fully immersed in the grout whilst mixing. Do not pull the paddle up and down whilst mixing.

Ensure there is no unmixed material left in the drum prior to placing the grout.

Important notice

A Safety Data Sheet (SDS) is available from the Fosroc website. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



constructive solutions

*Manufactured and sold under license from Fosroc International Limited. Fosroc, Conbextra and the Fosroc logo are trade marks of Fosroc International Limited, used under license.

Placing

The mixed grout should be poured steadily from one side only to eliminate the entrapment of air.

Continuous grout flow is essential. Sufficient grout must be available prior to starting.

The time taken to pour a batch should be regulated to the time taken to prepare the next batch.

Cleaning

All tools and equipment should be cleaned immediately after use with Solvent 10. Spillages should be absorbed with sand or sawdust and disposed in accordance with local regulations.

Limitations

During application

Grouting may be carried out without special precautions at ambient temperatures from 10°C to 35°C. Where temperatures exceed 20°C note the pot life will be reduced.

Cure temperatures below 15°C will result in slower strength build up; at 5°C cure will stop until the material warms.

Exotherm: All epoxy systems will develop a temperature rise on mixing. Its extent will be a function of the volume to surface ratio, the ambient temperature as well as the mass and thermal conductivity of the surrounding materials.

In service

The cured Conbextra EP120, which is completely resistant to frost and sub-zero temperatures, is suitable for use in service up to 55°C.

Supply

Conbextra EP120: 14 litre - 2 component pack

Conbextra EP120 Base: FC522333-11.3L

Conbextra EP120 Hardener: FC522444-2.7L

Storage

Conbextra EP120 base component has a shelf life of 12 months from date of manufacture if kept in a dry store in the original, unopened packaging.

Conbextra EP120 hardener component has a shelf life of 36 months from date of manufacture if kept in a dry store in the original, unopened packaging.

Parchem Construction Supplies Pty Ltd

1956 Dandenong Rd Clayton VIC 3168

Ph: 1800 812 864

www.fosroc.com.au

ABN 80 069 961 968

Distributed in New Zealand by: Concrete Plus Ltd

150 Hutt Park Road Gracefield Ph: 0800 657 156

www.fosroc.co.nz

NZBN 9429033691282