

Economical, Class A, shrinkage compensated grout - (gaps 10mm to 100mm)

Uses

Fosroc Construction Grout is used for general purpose grouting when completely filling concrete voids or grouting between a base plate and a substrate e.g. the grouting of a stanchion base plate.

Advantages

- Gaseous expansion system compensates for shrinkage and settlement in the plastic state
- Non-shrink according to ASTM C1107:2020
- High ultimate strength and low permeability ensure the durability of the hardened grout
- Can be dry packed, trowelled, poured and pumped
- No metallic iron content to cause staining
- Prepackaged material overcomes potential on-site batching variations
- RCS (Respirable Crystalline Silica) Hazard Free

Properties

Test Method	Standard	Result				
		Consistency	Water Addition	1 Day	7 Days	28 Days
Compressive Strength (MPa)	AS 1478.2:2005	Stiff	2.6	40	55	65
		Plastic	3.4	35	50	57
		Flowable	3.6	25	45	53
Flexural Strength (Modulus of Rupture) (MPa)	AS 1012.11 - 2000	Flowable	3.6	4.2	8.0	8.5
Indirect Tensile Strength (MPa)	AS 1012.10.2000	Flowable	3.6	2.9	4.7	6.0
Setting Time	ASTM C191:2021	4 hrs - initial set		5 hrs - final set		
VOC content	ASTM D3960-5	0.65g / litre				
Fresh Wet Density	ASTM C185:2020	2200 kg/m ³ - Flowable consistency				
Alkali reactive particles	Rapid Mortar Bar Test (RTA T363)	Non-reactive				
Flow Characteristics	AS 1478.2:2005	400 - 600mm (Flow Trough)				
Minimum Thickness		10mm				
Maximum Thickness		100mm				

Clarification of property values: The typical properties given above are derived from laboratory testing. Compressive strengths stated above were measured using cube samples. Test results obtained will vary if carried out to an alternative standard or sample dimensions are used.

Description

Fosroc Construction Grout, general purpose shrinkage compensated cementitious grout, is supplied as a ready to use dry powder. The addition of a controlled amount of clean water produces a flowing shrinkage compensated grout for gap thicknesses 10mm to 100mm.

Fosroc Construction Grout is a blend of Portland cement, graded fillers and chemical additives which impart controlled expansion in the plastic state whilst minimising water demand. The low water demand ensures high early strength. The graded filler is designed to assist uniform mixing and produce a consistent grout.

Fosroc Construction Grout is not hazardous in accordance with Australian Inventory of Industrial Chemicals. Contains <0.1% RCS.

Maximum aggregate size for pumping is 0.3mm.

Standards Compliance

AS 1478.2-2005 : Appendix E Test for Early Volume Change.

AS 1478.2-2005 : Tabel 4.1.2.2 Tests for Consistency.

Fosroc® Construction Grout

Test Results to ASTM Specification C1107: 2020

Test Method	Standard	Result	
Flow Consistency	ASTM C939:2016a	>104%	
Setting Time	ASTM C953:2017	Initial:	240 mins
		Final:	295 mins
Change in Height at Early Age at Final Setting Time	ASTM C827:2016	+0.24%	
Height Change of Hardened Grout Moist Cure	ASTM C1090:2015	1 day	+0.005%
		3 days	+0.005%
		14 days	+0.005%
		28 days	+0.005%
		28 days + 28 days in air	+0.005%
Compressive Strength	ASTM C109:2020b	1 day	25.5 N/mm ²
		3 days	46.6 N/mm ²
		7 days	62.7 N/mm ²
		28 days	70.2 N/mm ²

Note: All tests were carried out at 25°C ± 2°C until the age of the test. All above test results are independent third party results. Copies of these test results are available on request. The tests were carried out at a water addition rate of 3.6 litres per 20kg.

Flow properties of mixed grout

The flow distances given below in (mm) are intended as a guide. Actual flow distances will vary depending on site conditions:

Gap Depth (mm)	Flowable: 100mm head (mm)	Flowable: 250mm head (mm)
10	300	960
20	760	2080
30	1200	2400
40	1760	2400+
50	2400	2400+

Application Instructions

Preparation

Foundation surface

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. For maximum bond, surfaces should be abraded or roughened, preferably by mechanical means such as needle gun, grit blasting, grinding. Bolt holes or fixing pockets must be blown clean of any dirt or debris. These may need to be grouted beforehand.

Base plate

It is essential that this is clean and free from oil, grease scale or paint. Air pressure relief holes should be provided to allow venting of any isolated high spots.

Levelling shims

If these are to be removed after the grout has hardened, they should be treated with a thin layer of grease.

Formwork

The formwork should be constructed to be leakproof. This can be achieved by using foam rubber strip or sealant beneath the constructed formwork and between joints.

The formwork should include outlets for draining of pre-soaking water.

Unrestrained surface area

This must be kept to a minimum. Generally the gap width between the perimeter formwork and the plate edge should not exceed 150mm on the pouring side and 50mm on the opposite side. It is advisable where practical to have no gap at the flank sides.

Pre-soaking

Pre-soaking the formed grouting area with clean water helps to ensure good adhesion of the grout at the interface of the concrete foundation and improves the flow of the grout during the installation. The area should be filled with clean water for a **minimum 2 hours** before the grouting takes place.

Immediately before grouting takes place, any free water should be removed by draining or vacuum.

Particular care should be taken to blow out any bolt holes and pockets.

Mixing

A forced-action mixer is essential. Mix for 3 to 5 minutes at a slow speed (400/500rpm) in a suitably sized drum using appropriate equipment such as a 140mm helical mixing paddle fitted to a heavy-duty 1600W mixer.

Fosroc®

Construction Grout

The selected water content should be accurately measured into the mixing bucket. While mixing, slowly add the total contents of the Construction Grout bag, mix continuously for 5 minutes, ensuring a smooth, even consistency is obtained. Always add the powder to the water.

Required Consistency	Litres of water added per 20kg bag	Yield - litres of mixed material
Stiff	2.6 - 3.4	10.4
Plastic	3.4 - 3.6	10.7
Flowable	3.6 - 3.9	10.8

Mixing larger volumes

Larger quantities will require a high shear vane mixer. Do not use a colloidal impeller mixer.

Placing

At 23°C place the grout within 20 minutes of mixing to gain full benefit of the expansion process.

Construction Grout can be placed in thicknesses up to 100 mm in a single pour when used as an underplate grout. For thicker sections it is necessary to fill out Construction Grout with dry, well graded silt free, 5 to 6mm aggregate such as Conbextra Grout Aggregate to minimise heat build up.

Any bolt pockets must be grouted prior to grouting between the substrate and the base plate.

Continuous grout flow is essential. Sufficient grout must be prepared before starting. The time taken to pour a batch must be regulated to the time to prepare the next one.

Pouring should be from one side of the void to eliminate any air or pre-soaking water becoming trapped under the baseplate. It is advisable to pour the grout across the shortest distance of travel. The grout head must be maintained at all times so that a continuous grout front is achieved with no air entrapment.

Pumping

Where large volumes have to be placed Construction Grout may be pumped. A heavy duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps may also be suitable. Maximum aggregate size for pumping is 0.3mm. Ensure the selected pump is capable of pumping this size aggregate.

Important notice

A Safety Data Sheet (SDS) is available from the Fosroc website. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license.

Parchem Construction Supplies Pty Ltd

1956 Dandenong Rd Clayton VIC 3168
Ph: 1800 812 864
www.fosroc.com.au ABN 80 069 961 968
Distributed in New Zealand by: Concrete Plus Ltd
150 Hutt Park Road Gracefield Ph: 0800 657 156
www.fosroc.co.nz NZBN 9429033691282

Curing

On completion of the grouting operation, exposed areas should be thoroughly cured. This should be done by the use of **Concure** curing membrane, continuous application of water and/or wet hessian.

Cleaning

Construction Grout should be removed from tools and equipment with clean water immediately after use. Cured material can be removed mechanically.

Limitations

Low temperature working

When the air or contact surface temperatures are 10°C or below on a falling thermometer, warm water (30 - 40°C) is recommended to accelerate strength development.

For ambient temperatures below 10°C the formwork should be kept in place for at least 36 hours.

High temperature working

At ambient temperatures above 35°C cool water (below 23°C) should be used for mixing the grout prior to placement.

Supply

Supplied in 20kg moisture resistant plastic bags.

Fosroc Construction Grout 20kg: FC501000-20KG

Yield

Allowance should be made for wastage when estimating quantities required. The approximate yields are:

Consistency	Litres of mixed material
Stiff	10.4
Plastic	10.7
Flowable	10.8

Storage

Fosroc Construction Grout has a shelf life of 36 months from date of manufacture if kept in the original, unopened bags. Refer to the manufacture date indicated on the packaging.

Do not use if there are lumps in the product, or a loss of workability (requiring more water to be added) is experienced.