



Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 320823

### Report Information

**Submitting Organisation :** 00109358 : Parchem Construction Supplies Pty Ltd  
**Account :** 130335 : Parchem Construction Supplies Pty Ltd  
**AWQC Reference :** 130335-2021-CSR-1 : Prod Test: Conbextra GP (Organic Compounds & Metals)  
**Project Reference :** PT-4679  
**Product Designation :** Fosroc Conbextra GP - Cement Based Grout  
**Composition of Product :** Blend of Portland Cement, Graded Fillers and Chemical Additives.  
**Product Manufacturer :** Parchem Construction Supplies, Wyong, NSW, AUSTRALIA.  
**Use of Product :** In-Line/Cement Based Grout.  
**Sample Selection:** As provided by the submitting organisation.  
**Testing Requested :** **AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**  
**Product Type :** Composite  
**Samples :** Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018  
**Extracts :** Extracts were prepared as described in Appendix/Clause H, 6.8.  
**Project Completion Date :** 27-Sep-2021  
**Project Comment :** Thirty sequential soakings were performed to obtain a pH < 9.0. In accordance with section A8 (Cementitious Products).

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER

Michael Glasson  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 320823

### Summary of Results

APPENDIX/CLAUSE	RESULTS
H – Metals	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
6.8 – Organic Compounds	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.

### Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
H	TIC-006	EPA 200.8

### Organic Test Methods

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

**Summary Comment :** Refer to AWQC Project Reference PT-3466 (Test Report No. 232509) for additional test information.



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



**FINAL REPORT**

Report ID : 320823

**CLAUSE 6.7**

**Metals**

**Sample Description**

The sample consisted of a cementitious cube measuring 25 mm x 25 mm x 25 mm providing an approximate surface area of 15000 mm<sup>2</sup> per Litre. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature**

20°C ± 2°C.

**Test Method**

Metals (Appendix H)

**Scaling Factor**

Not applied.

**Method of Analysis**

All methods used to determine concentrations of metals are based on those described in the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
<b>Final Extract</b>					
Aluminium	0.001	0.027	0.024	0.023	0.2
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.01
Barium	0.0005	0.0266	0.0263	0.0262	0.7
Boron	0.020	<0.020	<0.020	<0.020	1.4
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	0.0001	0.0001	0.05
Copper	0.0001	0.1107	0.1178	0.1165	2.0
Iron	0.0005	0.0085	0.0094	0.0099	0.3
Lead	0.0001	0.0003	0.0005	0.0006	0.01
Manganese	0.0001	0.0006	0.0005	0.0005	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	0.0002	0.0002	0.0002	0.05
Nickel	0.0001	0.0015	0.0016	0.0015	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

**Evaluation**

The product passed the requirements of clause 6.7 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples**

1.

**Test Comment**

Not applicable.



Dzung Bui

APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



**FINAL REPORT**

Report ID : 320823

**CLAUSE 6.8 Organic Compounds**

**Sample Description** The sample consisted of a cementitious cube measuring 25 mm x 25 mm x 25 mm providing an approximate surface area of 15000 mm<sup>2</sup> per Litre. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported compounds have no guideline value.

**Scaling Factor** Not applied.

**Results**

**Organic Compound**

<b>Nitrosamines</b>	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2127025	ES2127025	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

**Organic Compound**

<b>Phenols</b>	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2127025	ES2127025	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 µg/L
2 4-dichlorophenol	<1.0	<1.0	200 µg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 µg/L
phenol	<1.0	<1.0	



Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

**FINAL REPORT**

Report ID : 320823

**Organic Compound**

Phthalate Esters	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2127025	ES2127025	
Bis(2-ethylhexyl) phthalate	<10	<10	10 µg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

**Organic Compound**

Polycyclic Aromatic Hydrocarbons	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2127025	ES2127025	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	



Corporate Accreditation No. 1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

**FINAL REPORT**

Report ID : 320823

**Organic Compound**

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
<b>Volatile Organic Compounds GCMS</b>			
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 µg/L
1 2-Dibromoethane	<1	<1	1 µg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 µg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 µg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 µg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	4	20	60 µg/L
Bromoform	1	5	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 µg/L
Chlorobenzene	<1	<1	300 µg/L
Chloroethane	<4	<4	
Chloroform	4	15	400 µg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	
Dibromochloromethane	4	21	150 µg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 µg/L
Ethylbenzene	<1	<1	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No. 1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 320823

### Organic Compound

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
<b>Volatile Organic Compounds GCMS</b>			
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 µg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 µg/L
Toluene	<1	<1	800 µg/L
Total 1,2-dichloroethene	<2	<2	60 µg/L
Total 1,3-dichloropropene	<2	<2	20 µg/L
Total Trichlorobenzene	<2	<2	30 µg/L
Total Xylene	<3	<3	600 µg/L
trans-1,3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	13	61	250 µg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

**Evaluation** The product passed the requirements of clause 6.8 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Subcontracted testing conducted by ALS, Environmental Division, NATA accreditation no. 825 site no. 10911 and ALS Scoresby, NATA accreditation no. 992, site no. 989

Qiong Huang

### APPROVED SIGNATORY



Corporate Accreditation No. 1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



## FINAL REPORT

Report ID : 232509

### Report Information

**Submitting Organisation** : 00109358 : Parchem Construction Supplies Pty Ltd  
**Account** : 130335 : Parchem Construction Supplies Pty Ltd  
**AWQC Reference** : 130335-2018-CSR-1 : Prod Test: Fosroc Conbextra GP - Cement Based Grout  
**Project Reference** : PT-3466  
**Product Designation** : Fosroc Conbextra GP - Cement Based Grout  
**Composition of Product** : Cement, Sand and Plasticiser.  
**Product Manufacturer** : Parchem Construction Supplies, Wyong, NSW, AUSTRALIA.  
**Use of Product** : In-Line/Cement Based Grout for Under Plate Grouting of Machine Base Plates.  
**Sample Selection** : As provided by the submitting organisation.  
**Testing Requested** : **AS/NZS 4020:2005 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**  
**Product Type** : Composite  
**Samples** : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2005  
**Extracts** : Extracts were prepared as described in Appendix C, D, E, F, G, H.  
**Project Completion Date** : 03-Sep-2018  
**Project Comment** : The results presented herein demonstrate compliance to AS/NZS 4020 for Fosroc Conbextra GP - Cement Based Grout at 20°C ± 2°C, exposed at an area to volume ratio up to 15,000 mm<sup>2</sup>/L.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER



Michael Glasson  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



## FINAL REPORT

Report ID : 232509

### Summary of Results

APPENDIX	RESULTS
C – Taste of Water Extract	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
D – Appearance of Water Extract	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
F – Cytotoxic Activity of Water Extract	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
G – Mutagenic Activity of Water Extract	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
H – Extraction of Metals	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.

### Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2130b
E	TO014-03	APHA 4500 O C
F	TM-001	AS/NZS 4020:2018
G	TM-002	AS/NZS 4020:2018
H	TIC-006	EPA 200.8

**Summary Comment :** Eleven sequential soakings were performed to obtain a pH < 9.0. In accordance with section A8 (Cementitious Products).

## FINAL REPORT

Report ID : 232509

### CLAUSE 6.2 Taste of Water Extract

<b>Sample Description</b>	The sample consisted of a single cementitious cylinder with a 62.5mm diameter and 56 mm height providing a total surface area of approximately 15,000 mm <sup>2</sup> /L. Extracts were prepared using 1130 mL volumes of pre-conditioning water(AI 12.6).
<b>Extraction Temperatur</b>	20°C ± 2°C.
<b>Test Method</b>	Taste of Water Extract (Appendix C)
<b>Test Information</b>	
<b>Scaling Factor</b>	Not applicable.
<b>Results</b>	Not detected (sample and controls).
<b>Evaluation</b>	The product passed the requirements of clause 6.2 when tested at an exposure of 15000 mm <sup>2</sup> per Litre.
<b>Number of Samples</b>	2.
<b>Test Comment</b>	Not applicable.



Peter Christopoulos  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 232509

### CLAUSE 6.3 Appearance of Water Extract

**Sample Description** The sample consisted of a single cementitious cylinder with a 62.5mm diameter and 56 mm height providing a total surface area of approximately 15,000 mm<sup>2</sup>/L. Extracts were prepared using 1130 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperatur** 20°C ± 2°C.

**Test Method** Appearance of Water Extract (Appendix D)

**Scaling Factor** Not applicable.


#### Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	1	5	HU
Turbidity	<0.1	0.5	NTU

**Evaluation** The product passed the requirements of clause 6.3 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Not applicable.



Andrew Ford  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 232509

### CLAUSE 6.4 Growth of Aquatic Micro-organisms

**Sample Description** The sample consisted of a single cementitious cylinder with a 62.5mm diameter and 56 mm height providing a total surface area of approximately 15,000 mm<sup>2</sup>/L. Extracts were prepared using 1130 mL volumes of test water.

**Test Method** Growth of Aquatic Micro-organisms (Appendix E)

**Inoculum** The volume of the inoculum was 100 mL

**Scaling Factor** Not applicable.

#### Results

Mean Dissolved Oxygen	Control	7.7 mg/L
Mean Dissolved Oxygen Differenc	Positive Reference	5.9 mg/L
	Negative Reference	0.1 mg/L
	Test	0.20 mg/L

**Evaluation** The product passed the requirements of clause 6.4 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Not applicable.



Thuy Diep  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 232509

### CLAUSE 6.5 Cytotoxic Activity of Water Extract

<b>Sample Description</b>	The sample consisted of a single cementitious cylinder with a 62.5mm diameter and 56 mm height providing a total surface area of approximately 15,000 mm <sup>2</sup> /L. Extracts were prepared using 1130 mL volumes of pre-conditioning water(AI 12.6).
<b>Extraction Temperatur</b>	20°C ± 2°C.
<b>Test Method</b>	Cytotoxic Activity of Water Extract (Appendix F)
<b>Scaling Factor</b>	Not applicable.
<b>Results</b>	Non-Cytotoxic.
<b>Evaluation</b>	The product passed the requirements of clause 6.5 when tested at an exposure of 15000 mm <sup>2</sup> per Litre.
<b>Number of Samples</b>	1.
<b>Test Comment</b>	The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Stella Fanok  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 232509

### CLAUSE 6.6 Mutagenic Activity of Water Extract

**Sample Description** The sample consisted of a single cementitious cylinder with a 62.5mm diameter and 56 mm height providing a total surface area of approximately 15,000 mm<sup>2</sup>/L. Extracts were prepared using 1130 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperatur** 20°C ± 2°C.

**Test Method** Mutagenic Activity of Water Extract (Appendix G)

**Scaling Factor** Not applicable.

#### Results

Bacteria Strain	Number of Revertants per Plate				
	S9	Blank	Sample Extract	Positive Controls	
<i>Salmonella typhimurium</i> TA98	-	26, 22, 19	18, 14, 9	1634, 1754, 1676	<u>NPD</u> (20µg)
Mean ± Standard deviation		22.3 ± 3.5	13.7 ± 4.5	1688.0 ± 60.9	
	+	34, 28, 25	17, 18, 16	2672, 2619, 2716	<u>2-AF</u> (20µg)
Mean ± Standard deviation		29.0 ± 4.6	17.0 ± 1.0	2669.0 ± 48.6	
<i>Salmonella typhimurium</i> TA100	-	32, 48, 12	50, 63, 48	2930, 1266, 687	<u>Azide</u> (1.0µg)
Mean ± Standard deviation		30.7 ± 18.0	53.7 ± 8.1	1627.7 ± 1164.4	
	+	96, 85, 68	82, 82, 82	613, 615, 476	<u>2-AF</u> (20µg)
Mean ± Standard deviation		83.0 ± 14.1	82.0 ± 0.0	568.0 ± 79.7	
<i>Salmonella typhimurium</i> TA102	-	196, 231, 220	73, 128, 125	1013, 785, 1100	<u>Mitomycin C</u> (10µg)
Mean ± Standard deviation		215.7 ± 17.9	108.7 ± 30.9	966.0 ± 162.7	
	+	449, 463, 438	456, 465, 451	1503, 2151, 2048	
Mean ± Standard deviation		450.0 ± 12.5	457.3 ± 7.1	1900.7 ± 348.2	

**Comments** S9 was used as a metabolic activator. NPD (4-nitro-o-phenylenediamine), Azide, and Mitomycin C are specific positive controls for strains TA98, TA100 and TA102 respectively while 2 - AF (2-aminofluorene) when used in conjunction with S9 is a positive control for both TA98 and TA100

**Evaluation** The product passed the requirements of clause 6.6 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Not applicable.



Peter Christopoulos  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

## FINAL REPORT

Report ID : 232509

### CLAUSE 6.7 Extraction of Metals

**Sample Description** The sample consisted of a single cementitious cylinder with a 62.5mm diameter and 56 mm height providing a total surface area of approximately 15,000 mm<sup>2</sup>/L. Extracts were prepared using 1130 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Extraction of Metals (Appendix H)

**Scaling Factor** Not applicable.

**Method of Analysis** All methods used to determine concentrations of metals are based on those described in the 21st edition of Standard Methods for the Examination of Water and Wastewater published by the APHA, AWWA and WEF (2005). The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre. Concentration of the metals described in Table 2 of the AS/NZS 4020:2005 are determined as follows:

Antimony, Arsenic, Barium, Cadmium, Chromium, Copper, Lead, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
<b>Final Extract</b>					
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	0.0004	0.0004	0.0003	0.007
Barium	0.0005	0.0280	0.0279	0.0276	0.7
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	0.0002	0.0002	0.0002	0.05
Copper	0.0001	0.0983	0.1118	0.1103	2.0
Lead	0.0001	0.0005	0.0009	0.0008	0.01
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	0.0003	0.0003	0.0003	0.05
Nickel	0.0001	0.0008	0.0017	0.0010	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

**Evaluation** The product passed the requirements of clause 6.7 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Not applicable.



Dzung Bui  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025