Email: producttesting@awgc.com.au



FINAL REPORT

Internet: www.awgc.com.au

Report ID: 339139

Report Information

Submitting Organisation: 00109358 : Parchem Construction Supplies Pty Ltd

Account: 130335 : Parchem Construction Supplies Ptv Ltd

AWQC Reference: 130335-2022-CSR-1: Prod Test: Fosroc Nitoseal PU250

Project Reference: PT-4873

Product Designation: Fosroc Nitoseal PU250 - Polyurethane Joint Sealant.

Composition of Product : Polyurethane Polymer.

Product Manufacturer: Parchem Construction Supplies, Wyong, NSW, AUSTRALIA.

Use of Product : In-Line/Polyurethane Joint Sealant.

Sample Selection: As provided by the submitting organisation.

Testing Requested: AS/NZS 4020:2018 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING

WATER

Product Type: Composite

Samples: Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018

Extracts: Extracts were prepared as described in Appendix/Clause C, D, E, F, G, H, 6.8.

Project Completion Date : 30-May-2022

Project Comment: Product sample received in the week 23-Feb-2022 and testing commenced 09-Mar-2021.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING TO ASNZS 4020:2018. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER







- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

250 Victoria Square Adelaide SA 5000

Email: producttesting@awqc.com.au

Tel: 1300 653 366

Fax: 1300 883 171



FINAL REPORT

Internet: www.awgc.com.au

Report ID: 339139

Summary of Results

APPENDIX/CLAUSE	RESULTS
C - Taste	Passed at an exposure of 2500 mm² per Litre.
D - Appearance	Passed at an exposure of 2500 mm² per Litre.
E - Growth of Aquatic Micro-organisms	Passed at an exposure of 2500 mm² per Litre.
F — Cytotoxic Activity	Passed at an exposure of 2500 mm² per Litre.
G - Mutagenic Activity	Passed at an exposure of 2500 mm² per Litre.
H - Metals	Passed at an exposure of 2500 mm² per Litre.
6.8 — Organic Compounds	Passed at an exposure of 2500 mm² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	NATA Accredited
С	T0320-01	Y
D	TO029-01 & TO018-01	Y
Е	TO014-03	Y
F	TM-001	Y
G	TM-002	Y
Н	TIC-006	Υ

Organic Test Methods

Test(s) in Clause	Test Method	NATA Accredited
Clause 6.8	TMZ-M36	Y
	EP239	Υ
	EP132-LL	Υ
	EP075C	Υ
	EP075ASIM	Y





1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval

2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

 $\underline{\verb§||} \verb|| ttps://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>||}$

PO Box 1751 250 Victoria Square Adelaide SA 5001 Adelaide SA 5000 Tel: 1300 653 366 Fax: 1300 883 171



Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 339139

Laboratory Information

Laboratory	NATA accreditation ID
Product Testing	1115
Australian Laboratory Services Pty Ltd - New South Wales	825,992
Inorganic Chemistry - Physical	1115
Organic Chemistry	1115
Protozoology	1115
Inorganic Chemistry - Metals	1115
Inorganic Chemistry - Waste Water	1115

Summary Comment:

Not applicable.





- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- $\underline{\ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ \ \ }\underline{\ \ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ \ }\underline{\ \ \ }\underline{\ \ \ \ }\underline{\ \ \$

Email: producttesting@awqc.com.au



Internet: www.awqc.com.au

FINAL REPORT

Report ID: 339139

CLAUSE 6.2 Taste

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a

total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000

mL volumes of 50 mg/L hardness water.

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Taste (Appendix C)

Test Information

Scaling Factor Not applied.

Results Not detected (sample and controls).

Evaluation The product passed the requirements of clause 6.2 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 2.

Test Comment Not applicable.

Michael Glasson APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- . 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>

Email: producttesting@awqc.com.au



Internet: www.awqc.com.au

FINAL REPORT

Report ID: 339139

CLAUSE 6.3 Appearance

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a

total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000

mL volumes of 50 mg/L hardness water.

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Appearance (Appendix D)

Scaling Factor Not applied.

Results

	Test (- Blank)	Maximum Allowed	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 1.

Test Comment Not applicable.

Andrew Ford
APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- . 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>

AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 339139

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a

total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000

mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor Not applied.

Results

Mean Dissolved Oxygen Control 7.4 mg/L

Mean Dissolved Oxygen Difference Positive Reference 5.9 mg/L

Negative Reference <0.1 mg/L

Test 1.70 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 1.

Test Comment Not applicable.

Thuy Diep
APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

Email: producttesting@awqc.com.au



FINAL REPORT

Internet: www.awgc.com.au

Report ID: 339139

CLAUSE 6.5 Cytotoxic Activity

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a

total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000

mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Cytotoxic Activity (Appendix F)

Scaling Factor Not applied.

Results 24 HR Non-cytotoxic response, healthy cell morphology with <30% cell death

48 HR Non-cytotoxic response, healthy cell morphology with <30% cell death

72 HR Non-cytotoxic response, healthy cell morphology with <30% cell death

Blank Control Results Blank; non-cytotoxic response, healthy cell morphology with <30% cell death

Positive Control Results Positive control; Cytotoxic response, unhealthy cell morphology with >70% cell death

The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition

zinc sulphate (0.4 mmol) was used for the positive control in the analysis.

Evaluation The product passed the requirements of clause 6.5 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 1.

Test Comment Not applicable.

Stella Fanok APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at



Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 339139

CLAUSE 6.6 Mutagenic Activity

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a

total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000

mL volumes of 50 mg/L hardness water.

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Mutagenic Activity (Appendix G)

Scaling Factor Not applied.

Results

Bacteria Strain Number of Revertants per Plate

		S9	Blank	Sample Extract	Positive Controls	
Salmonella	typhimurium TA98	-	34, 26, 34	26, 23, 25	1500, 1394, 1481	<u>NPD (</u> 20μg)
Mear	t ± Standard deviation		31.3 ± 4.6	24.7 ± 1.5	1458.3 ± 56.5	
		+	30, 34, 25	29, 31, 29	3354, 3119, 3147	<u>2-AF (</u> 20μg)
Mear	t ± Standard deviation		29.7 ± 4.5	29.7 ± 1.2	3206.7 ± 128.4	
Salmonella	typhimurium TA102	-	169, 203, 209	173, 184, 217	1760, 1804, 1722	Mitomycin C(10μg)
Mear	ı ± Standard deviation		193.7 ± 21.6	191.3 ± 22.9	1762.0 ± 41.0	
		+	208, 212, 242	221, 186, 220	1466, 1739, 1938	
Mear	n ± Standard deviation		220.7 ± 18.6	209.0 ± 19.9	1714.3 ± 237.0	

The differences in the mean number of revertants between the blank and test extracts do not exceed two standard deviations; accordingly, there is no evidence of a mutagenic response.

Comments S9 was used as the metabolic activator. NPD (4-nitro-o-phenylenediamine) and Mitomycin

C are specific positive controls for strains TA98 - and TA102 (- and +) respectively, while 2-AF (2-aminofluorene) when used in conjunction with S9 is a positive control for TA98+.

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 1.

Test Comment Not applicable.

Michael Glasson APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

uare Tel: 1300 653 366 000 Fax: 1300 883 171

Email: producttesting@awqc.com.au



Internet: www.awqc.com.au FINAL REPORT

Report ID: 339139

CLAUSE 6.7 Metals

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a

total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000

mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Metals (Appendix H)

Scaling Factor Not applied.

Method of Analysis Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined

as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled

Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Aluminium	0.001	0.028	0.005	0.005	0.2
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	0.0003	< 0.0003	< 0.0003	0.01
Barium	0.0005	0.0278	<0.0005	<0.0005	0.7
Boron	0.020	<0.020	<0.020	<0.020	1.4
Cadmium	0.0001	< 0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	0.0003	<0.0001	<0.0001	0.05
Copper	0.0001	0.0477	< 0.0001	< 0.0001	2.0
Iron	0.0005	0.0042	< 0.0005	< 0.0005	0.3
Lead	0.0001	0.0007	< 0.0001	< 0.0001	0.01
Manganese	0.0001	0.0008	<0.0001	<0.0001	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	0.0003	< 0.0001	< 0.0001	0.05
Nickel	0.0001	0.0012	< 0.0001	< 0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation The product passed the requirements of clause 6.7 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 1.

Test Comment Not applicable.

Dzung Bui APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

Email: producttesting@awgc.com.au



FINAL REPORT

Internet: www.awgc.com.au

Report ID: 339139

CLAUSE 6.8 Organic Compounds

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total

surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL

volumes of 50 mg/L hardness water.

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Organic Compounds (Clause 6.8). The maximum allowed (Max Allowed) values are taken from

the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please

note, some reported compounds have no guideline value.

Scaling Factor Not applied.

Results

Organic Compound

Nitrosamines	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2210146	ES2209659	
1-Nitrosopiperidine (NPip)	<0.003	< 0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	< 0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	< 0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	< 0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	< 0.003	

Organic Compound

Organic Compound			
Phenois	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2210146	ES2209659	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 μg/L
2 4-dichlorophenol	<1.0	<1.0	200 µg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 μg/L
phenol	<1.0	<1.0	





- Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>

Corporate Accreditation No.1115



Internet: www.awgc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 339139

npound
1

Phthalate Esters	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2210146	ES2209659	
Bis(2-ethylhexyl) phthalate	<10	<10	10 μg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

0

Di-n-octyl phthalate	<2	<2	
Organic Compound			
Polycyclic Aromatic Hydrocarbons	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2210146	ES2209659	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	





1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval

2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

Corporate Accreditation No.1115

Chemical and Biological Testing



Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 339139

Organic Compound

Organic Compound			
Volatile Organic Compounds GCMS	Blank	Test	Max Allowed
	μg/L	μg/L	
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 μg/L
1 2-Dibromoethane	<1	<1	1 μg/L
1 2-Dichlorobenzene	<1	<1	1500 μg/L
1 2-Dichloroethane	<1	<1	3 μg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 μg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 μg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	29	1	60 μg/L
Bromoform	5	<1	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 μg/L
Chlorobenzene	<1	<1	300 μg/L
Chloroethane	<4	<4	
Chloroform	26	3	400 μg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	"
Dibromochloromethane	26	<1	150 μg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 μg/L
Ethylbenzene	<1	<1	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be
 - considered. Measurement uncertainty is available at https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>

AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 339139

Organic Compound

Volatile Organic Compounds GCMS	IS Blank	Test	Max Allowed
	μg/L	μg/L	
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 μg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 μg/L
Toluene	<1	<1	800 μg/L
Total 1 2-dichloroethene	<2	<2	60 μg/L
Total 1 3-dichloropropene	<2	<2	20 μg/L
Total Trichlorobenzene	<2	<2	30 μg/L
Total Xylene	<3	<3	600 μg/L
trans-1 3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	86	4	250 μg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation The product passed the requirements of clause 6.8 when tested at an exposure of 2500 mm²

per Litre.

Number of Samples 1.

Test Comment Not applicable.

Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- measurement-uncertainty