AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client :	Parchem Construction Supplies Pty Ltd	**Test Number :**	21-001303
	7 Lucca Road	**Issue Date :**	8/04/2021
	Wyong NSW 2164	**Print Date :**	8/09/2021

Sample Description

Clients Ref :   "Nitoflor N with Grit"
Resin applied to cement sheet
End Use :   Floor coating

AS 4586-2013
Appendix A

Slip Resistance Classification of new Pedestrian Surface Materials
Wet Pendulum Test Method

Date of Testing					07/04/2021	
Test Temperature (20±5degC)					22	°C
Sample Preparation	Washed with pH neutral dtergent and dried.					
Test Direction	Length					
Fixed/Unfixed					Unfixed	

Slider No 96 Batch No					95	
Length	1	2	3	4	5	SRV
British Pendulum Number	39	39	39	39	41	39
Classification					P3	

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01   Calibrated 08/11/2019
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions , including maintenance and wear on their slip resistance be checked.

Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

0204/11/06