

FINAL REPORT

Report ID : 248733

Report Information

Submitting Organisation : 00109358 : Parchem Construction Supplies Pty Ltd
Account : 130335 : Parchem Construction Supplies Pty Ltd
AWQC Reference : 130335-2018-CSR-3 : Prod Test: Emer-Seal CR/Fosroc Nitroseal SC600
Project Reference : PT-3759
Product Designation : Emer-Seal CR/Fosroc Nitroseal SC600
Composition of Product : Silicone Sealant.
Product Manufacturer : Parchem Construction Supplies, Wyong, NSW, AUSTRALIA.
Use of Product : In-Line/Chemical Resistant Elastomeric Sealant.
Sample Selection : As provided by the submitting organisation.
Testing Requested : **AS/NZS 4020:2005 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2005
Extracts : Extracts were prepared as described in Appendix C, D, E, F, G, H.
Project Completion Date : 29-Mar-2019
Project Comment : The results presented herein demonstrate compliance of Emer-Seal CR/Fosroc Nitroseal SC600 to AS/NZS 4020 when exposed at area to volume ratios up to 2500 mm²/L at 20°C ± 2°C.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 248733

Summary of Results

APPENDIX	RESULTS
C – Taste of Water Extract	Passed at an exposure of 2500 mm ² per Litre.
D – Appearance of Water Extract	Passed at an exposure of 2500 mm ² per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 2500 mm ² per Litre.
F – Cytotoxic Activity of Water Extract	Passed at an exposure of 2500 mm ² per Litre.
G – Mutagenic Activity of Water Extract	Passed at an exposure of 2500 mm ² per Litre.
H – Extraction of Metals	Passed at an exposure of 2500 mm ² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2130b
E	TO014-03	APHA 4500 O C
F	TM-001	AS/NZS 4020:2018
G	TM-002	AS/NZS 4020:2018
H	TIC-006	EPA 200.8

Summary Comment :

The sealant was applied (to acid etched glass slides) and cured for 7 days at 20°C prior to testing.

FINAL REPORT

Report ID : 248733

CLAUSE 6.2 Taste of Water Extract

Sample Description	The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total surface area of approximately 2500 mm ² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.
Extraction Temperatur	20°C ± 2°C.
Test Method	Taste of Water Extract (Appendix C)
Test Information	
Scaling Factor	Not applied.
Results	Not detected (sample and controls).
Evaluation	The product passed the requirements of clause 6.2 when tested at an exposure of 2500 mm ² per Litre.
Number of Samples	2.
Test Comment	Not applicable.



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 248733

CLAUSE 6.3 Appearance of Water Extract

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperatur 20°C ± 2°C.

Test Method Appearance of Water Extract (Appendix D)

Scaling Factor Not applied.


Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 2500 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Andrew Ford
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 248733

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor Not applied.

Results

Mean Dissolved Oxygen	Control	7.4 mg/L
Mean Dissolved Oxygen Differenc	Positive Reference	5.6 mg/L
	Negative Reference	<0.1 mg/L
	Test	<0.10 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 2500 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Thuy Diep
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 248733

CLAUSE 6.5 Cytotoxic Activity of Water Extract

Sample Description	The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total surface area of approximately 2500 mm ² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.
Extraction Temperatur	20°C ± 2°C.
Test Method	Cytotoxic Activity of Water Extract (Appendix F)
Scaling Factor	Not applied.
Results	Non-cytotoxic.
Evaluation	The product passed the requirements of clause 6.5 when tested at an exposure of 2500 mm ² per Litre.
Number of Samples	1.
Test Comment	The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Stella Fanok
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 248733

CLAUSE 6.6 Mutagenic Activity of Water Extract

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperatur 20°C ± 2°C.

Test Method Mutagenic Activity of Water Extract (Appendix G)

Scaling Factor Not applied.

Results

Bacteria Strain	Number of Revertants per Plate				
	S9	Blank	Sample Extract	Positive Controls	
<i>Salmonella typhimurium</i> TA98	-	21, 32, 22	32, 17, 20	4131, 4026, 4234	<u>NPD</u> (20µg)
Mean ± Standard deviation		25.0 ± 6.1	23.0 ± 7.9	4130.3 ± 104.0	
	+	18, 16, 19	13, 19, 29	3784, 4022, 3846	<u>2-AF</u> (20µg)
Mean ± Standard deviation		17.7 ± 1.5	20.3 ± 8.1	3884.0 ± 123.5	
<i>Salmonella typhimurium</i> TA100	-	147, 115, 119	121, 111, 125	900, 917, 912	<u>Azide</u> (1.0µg)
Mean ± Standard deviation		127.0 ± 17.4	119.0 ± 7.2	909.7 ± 8.7	
	+	126, 116, 140	141, 136, 158	2408, 2344, 2187	<u>2-AF</u> (20µg)
Mean ± Standard deviation		127.3 ± 12.1	145.0 ± 11.5	2313.0 ± 113.7	
<i>Salmonella typhimurium</i> TA102	-	407, 448, 525	503, 423, 472	3408, 3692, 3046	<u>Mitomycin C</u> (10µg)
Mean ± Standard deviation		460.0 ± 59.9	466.0 ± 40.3	3382.0 ± 323.8	
	+	445, 518, 466	510, 507, 522	2204, 2471, 2285	
Mean ± Standard deviation		476.3 ± 37.6	513.0 ± 7.9	2320.0 ± 136.9	

Comments S9 was used as a metabolic activator. NPD (4-nitro-o-phenylenediamine), Azide, and Mitomycin C are specific positive controls for strains TA98, TA100 and TA102 respectively while 2 - AF (2-aminofluorene) when used in conjunction with S9 is a positive control for both TA98 and TA100

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 2500 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 248733

CLAUSE 6.7 Extraction of Metals

Sample Description The sealant was applied onto a single sided glass substrate (25mm x 100mm) providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Extraction of Metals (Appendix H)

Scaling Factor Not applied.

Method of Analysis All methods used to determine concentrations of metals are based on those described in the 21st edition of Standard Methods for the Examination of Water and Wastewater published by the APHA, AWWA and WEF (2005). The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre. Concentration of the metals described in Table 2 of the AS/NZS 4020:2005 are determined as follows:

Antimony, Arsenic, Barium, Cadmium, Chromium, Copper, Lead, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.007
Barium	0.0005	<0.0005	<0.0005	<0.0005	0.7
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	<0.0001	<0.0001	<0.0001	2.0
Lead	0.0001	<0.0001	<0.0001	<0.0001	0.01
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	<0.0001	<0.0001	<0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation The product passed the requirements of clause 6.7 when tested at an exposure of 2500 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Dzung Bui
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025